

Aktivkohle · Activated Carbon · Charbon Actif  
Carbon Activado · Carbone Attivo

® **Carbopal PA 4**

Powdered activated carbon

**Specifications:**

Moisture content (wt.%) (as packed)	< 12
Ash content (wt.%)	< 5
pH-value	2 - 5
Molasses factor	0,4 - 0,5

**Typical characteristics:**

Total surface area (m <sup>2</sup> /g) (BET-method)	> 1250
Iodine adsorption (mg/g)	1300
Methylene blue value (ml)	17
Wet screen analysis (wt.%) < 40 µm	approx. 70

**The activated carbon meets the requirements of the Food Chemicals Codex (5th edition, 2003).**

**Remarks:**

The above data are based on test methods of Donau Carbon.  
Copies are available upon request.

e0911/03

**Donau Carbon GmbH & Co. KG**

Gwinnerstr. 27-33  
60388 Frankfurt am Main, Germany

Telefon +49(0)69 4011-426  
Telefax +49(0)69 4011-659

**Unser QM-System ist zertifiziert - Our QM-system is certified**

