

BLUESILTM
FLD 47 V 50 to 47 V 1000

Description	BLUESIL FLD 47 V 50 to 47 V 1000 are straight chained polydimethylsiloxanic fluids.
Examples of applications	BLUESIL FLD 47 V 50 to 47 V 1000 are used as: <ul style="list-style-type: none">• Thermostatic fluids (– 50 °C to + 200 °C).• Dielectric fluids (impregnation of paper for condensers).• Anti-blotting products for photocopying machines.• Thinning and plastifying agents for RTV's and silicone sealants.• Lubricating and heat protecting agents for textile threads (synthetic sewing threads).• Ingredients in maintenance products (polishes, wax polishes, floor and furniture polishes, etc.).• Paint additives (anti-cratering, anti-floating/flooding and anti-scratching effects, etc.).• Water repellent treatment :<ul style="list-style-type: none">- of powders (for paints and plastics),- of fibres : glass fibres.• Release agents (mould release of plastics and metal castings).• Lubricants (lubrication of elastomers or plastics on metals).• Surfactants for styrene-butadiene foam.
Advantages	BLUESIL FLD 47 V 50 to 47 V 1000 have the following properties: <ul style="list-style-type: none">• Very good resistance to high and low temperature.• Good combustion resistance.• Good dielectric properties.• Low surface tension.• High compressibility.• Absence of ageing upon exposure to atmospheric agents.• Good oxidation resistance.• Little change in viscosity with temperature.• Good resistance to high and prolonged shear stress.

BLUESIL™ FLD 47 V 50 to 47 V 1000

Characteristics

Properties	BLUESIL FLD					
	47V50	47V100	47V300	47V350	47V500	47V1000
Appearance	Colourless, limpid liquid					
Viscosity at 25 °C, mm ² /s, approx.	50	100	300	350	500	1000
Specific gravity at 25 °C, approx.	0.959	0.965	0.970	0.970	0.970	0.970
Flash point (closed cup), °C, approx.	280	≥ 300	≥ 300	≥ 300	≥ 300	≥ 300
Freezing point, °C, approx.	- 55	- 55	- 50	- 50	- 50	- 50
Refractive index at 25 °C, approx.	1.402	1.403	1.403	1.403	1.403	1.403
Surface tension at 25 °C, mN/m, approx.	20.7	20.9	21.1	21.1	21.1	21.1
Vapour pressure at 200 °C, Pa, approx.	1.33	1.33	1.33	1.33	1.33	1.33
Volume expansion coeff. between 25 and 100 °C, approx. .	1.05.10 ⁻³	9.45.10 ⁻⁴	9.45.10 ⁻⁴	9.45.10 ⁻⁴	9.45.10 ⁻⁴	9.45.10 ⁻⁴
Specific heat capacity between 40 and 200°C, J/g, °C	1.46	1.46	1.46	1.46	1.46	1.46
Thermal conductivity, W/m°C, approx.	0.16	0.16	0.16	0.16	0.16	0.16
Viscosity / temperature coeff. (1), approx.	0.59	0.60	0.62	0.62	0.62	0.62
Dielectric strength at 25 °C, kV/mm, approx.	15	16	16	16	16	16
Dielectric constant at 25 °C between 0.5 and 100 kHz, approx.	2.80	2.80	2.80	2.80	2.80	2.80
Power factor at 25 °C, at 100 kHz, approx.	1.10 ⁻⁴	1.10 ⁻⁴	1.10 ⁻⁴	1.10 ⁻⁴	1.10 ⁻⁴	1.10 ⁻⁴
Permittivity at 25 °C, Ω.cm, approx.	1.10 ¹⁴	1.10 ¹⁵	1.10 ¹⁵	1.10 ¹⁵	1.10 ¹⁵	1.10 ¹⁵

(1) Viscosity / temperature coefficient = 1 - (viscosity at 100 °C / viscosity at 40 °C)

Packaging

BLUESIL FLD 47 V 50 to 47 V 1000 are available in 25 and 200 kg drums, in 1000 kg containers or in 20 tonnes tankers.

BLUESIL™ FLD 47 V 50 to 47 V 1000

Storage and shelf life

When stored in its original unopened packaging at a temperature of between – 20 and + 50 °C, **BLUESIL FLD 47 V 50 to 47 V 1000** may be stored for up to 3 years from its date of manufacture (expiry date). Comply with the storage instructions and expiry date marked on the packaging.

Past this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.

Safety

Consult the Safety Data Sheet for **BLUESIL FLD 47 V 50 to 47 V 1000**.

Visit our website www.bluestarsilicones.com

EUROPE

Bluestar Silicones France
21 Avenue Georges Pompidou
F69486 Lyon Cedex 03
FRANCE
Tel. (33) 4 72 13 19 00
Fax (33) 4 72 13 19 88

NORTH AMERICA

Bluestar Silicones USA
2 Tower Center Boulevard
Suite 1601
East Brunswick, NJ 08816-1100
United States
Tel. (1) 732 227-2060
Fax. (1) 732 249-7000

LATIN AMERICA

Bluestar Silicones Brazil Ltda.
Av. Maria Coelho Aguiar, 215
Bloco G – 1º andar
05804-902-Sao Paulo – SP-
Brazil
Tel. (55) 11 37477887

ASIA PACIFIC

Bluestar Silicones Hong Kong
Trading Co. Ltd
29th Floor, 88 Hing Fat Street
Causeway Bay
Hong Kong
Tel. (852) 3106 8200
Fax (852) 2979 0241

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.